



08/25/00

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Page 1 of 3

REQUEST FOR FILING APPLICATION

Under Rule 53(a), (b) & (f)

(No Filing Fee or Oath/Declaration)

(Do NOT use for Provisional or PCT Applications)

Use for Design or Utility Applications

PATENT
APPLICATION

RULE 53(f) NO DECLARATION

Assistant Commissioner of Patents
and Trademarks
Washington, DC 20231

Atty. Dkt.

PM 271649

M#

990090 RS

Client Ref

Date:

August 25, 2000

Sir:

1. This is a Request for filing a new Patent Application (☐ Design ☒ Utility) entitled:

2. (Complete) Title:

FURNACE CARBON BLACK,
PROCESS FOR PRODUCTION AND USE THEREOF


without a filing fee or Oath/Declaration but for which is enclosed the following:

3. ☒ Abstract 1 page(s).4. 14 Pages of Specification (only spec. and claims); 5. ☐ Specification in non-English language6. 5 Numbered claim(s); and7. ☒ Drawings: 2 sheet(s) ☐ 1 set informal; 8. ☒ formal of size: ☒ A4 ☐ 11"9. **DOMESTIC/INTERNATIONAL** priority is claimed under 35 USC 119(e)/120/365(c) based on the following provisional, nonprovisional and/or PCT international application(s):

Application No.	Filing Date	Application No.	Filing Date
(1)		(2)	
(3)		(4)	
(5)		(6)	

10. **FOREIGN** priority is claimed under 35 USC 119(a)-(d)/365(b) based on filing in Europe

Application No.	Filing Date	Application No.	Filing Date
(1) 99116930.1	27 August 1999	(2)	
(3)		(4)	
(5)		(6)	

11. 1 (No.) Certified copy (copies): ☒ attached; ☐ previously filed (date) _____
in U.S. Application No. / filed on _____12. ☐ This is a reissue of Patent No. _____13. ☐ See top first page re prior Provisional, National, International application(s) (X box only if info is there and do not complete corresponding item 14 or 15.)14. ☐ **Amend the specification** by inserting before the first line -- This is a ☐ Continuation-in-Part
☐ Divisional ☐ Continuation ☐ Substitute Application (MPEP 201.09) of:14(a) ☐ National Appln. No. / filed .- - (M#)14(b) ☐ International Appln. No. PCT/ filed which designated the U.S. - -15. ☐ **Amend the specification** by inserting before the first line: --This application claims the benefit of U.S. Provisional Application No. 60/ , filed --16. Extension to date: ☐ concurrently filed ☐ not needed ☐ previously filed

17. ☐ Prior application is assigned to

by Assignment recorded _____ Reel _____ Frame _____

18. ☐ Attached:

19. This application is made by the following named inventor(s) (Double check instructions for accuracy.):

(1) Inventor	Karl		VOGEL
	First	Middle Initial	Family Name
Residence	Alzenau	Germany	Germany
	City	State/Foreign Country	Country of Citizenship
Post Office Address	Am Mittelbach 9, DE-63755 Alzenau, Germany		
(include Zip Code)			

(2) Inventor	Emmanuel		AUER
	First	Middle Initial	Family Name
Residence	Frankfurt	Germany	Germany
	City	State/Foreign Country	Country of Citizenship
Post Office Address	Rennbahnstrasse 50, DE-60528 Frankfurt, Germany		
(include Zip Code)			

(3) Inventor	Karl-Anton		STARZ
	First	Middle Initial	Family Name
Residence	Rodenbach	Germany	Germany
	City	State/Foreign Country	Country of Citizenship
Post Office Address	Adolf-Reichwein-Strasse 12, DE-63517 Rodenbach, Germany		
(include Zip Code)			

(4) Inventor	Peter		ALBERS
	First	Middle Initial	Family Name
Residence	Hanau	Germany	Germany
	City	State/Foreign Country	Country of Citizenship
Post Office Address	Kleinfellerstrasse 3, DE-63454 Hanau, Germany		
(include Zip Code)			

(5) Inventor	Klaus		BERGEMANN
	First	Middle Initial	Family Name
Residence	Erlensee	Germany	Germany
	City	State/Foreign Country	Country of Citizenship
Post Office Address	Bruchköbeler Strasse 27, DE-63526 Erlensee, Germany		
(include Zip Code)			

20. NOTE: FOR ADDITIONAL INVENTORS, check box ☒ and attach sheet with same information regarding additional inventors.

Pillsbury Madison & Sutro LLP
Intellectual Property Group

1100 New York Avenue, NW.
Ninth Floor
Washington, DC 20005-3918
Tel: (202) 861-3000
Atty/Sec: RNM/LMR

By: Atty: Ruth N. Morduch

Reg. No. 31044

Sig:

Ruth N. Morduch

Fax: (202) 822-0944
Tel: (202) 861-3617

NOTE: File in duplicate with 2 post card receipts (PAT-103) & attachments

REQUEST FOR FILING APPLICATION
Under Rule 53(a), (b)(1) & (d)(1)
(Continued : Additional Inventors)

(6) Inventor	Conny		VOGLER
	First	Middle Initial	Family Name
Residence	Bornheim	Germany	Germany
	City	State/Foreign Country	Country of Citizenship
Post Office Address	Königsberger Strasse 17, DE-53332 Bornheim, Germany		
(include Zip Code)			

(7) Inventor			
	First	Middle Initial	Family Name
Residence			
	City	State/Foreign Country	Country of Citizenship
Post Office Address			
(include Zip Code)			

(8) Inventor			
	First	Middle Initial	Family Name
Residence			
	City	State/Foreign Country	Country of Citizenship
Post Office Address			
(include Zip Code)			

(9) Inventor			
	First	Middle Initial	Family Name
Residence			
	City	State/Foreign Country	Country of Citizenship
Post Office Address			
(include Zip Code)			

(10) Inventor			
	First	Middle Initial	Family Name
Residence			
	City	State/Foreign Country	Country of Citizenship
Post Office Address			
(include Zip Code)			

(11) Inventor			
	First	Middle Initial	Family Name
Residence			
	City	State/Foreign Country	Country of Citizenship
Post Office Address			
(include Zip Code)			

(12) Inventor			
	First	Middle Initial	Family Name
Residence			
	City	State/Foreign Country	Country of Citizenship
Post Office Address			
(include Zip Code)			

APPLICATION UNDER UNITED STATES PATENT LAWS

Atty. Dkt. No. PM 271649
(M#)

Invention: FURNACE CARBON BLACK, PROCESS FOR PRODUCTION AND USE THEREOF

Inventor (s): Karl VOGEL
Emmanuel AUER
Karl-Anton STARZ
Peter ALBERS
Klaus BERGEMANN
Conny VOGLER

Pillsbury Madison & Sutro LLP
Intellectual Property Group
1100 New York Avenue, NW
Ninth Floor
Washington, DC 20005-3918
Attorneys
Telephone: (202) 861-3000

This is a:

- ☐ Provisional Application
- ☒ Regular Utility Application
- ☐ Continuing Application
 - ☒ The contents of the parent are incorporated by reference
- ☐ PCT National Phase Application
- ☐ Design Application
- ☐ Reissue Application
- ☐ Plant Application
- ☐ Substitute Specification
 - Sub. Spec Filed _____
 - in App. No. _____ / _____
- ☐ Marked up Specification re
 - Sub. Spec. filed _____
 - In App. No _____ / _____

SPECIFICATION

[illegible]

5

10

15

30

If the carbon black oil is divided between two different injection points which are offset relative to each other along the axis of the reactor, then at the

first, upstream point, the amount of residual oxygen still contained in the combustion chamber waste gas is present in excess relative to the carbon black oil that is sprayed in. Accordingly, carbon black formation takes place at a higher temperature at that point as compared with subsequent carbon black injection sites, that is to say the carbon blacks formed at the first injection point are always more finely divided and have a higher specific surface area than those formed at a subsequent injection point. Each further injection of carbon black oils leads to further temperature reductions and to carbon blacks having larger primary particles. Carbon blacks produced in this manner therefore exhibit a broadening of the aggregate size distribution curve and, after incorporation into rubber, show different behavior than carbon blacks having a very narrow monomodal aggregate size spectrum. The broader aggregate size distribution curve leads to a lower loss factor of the rubber mixture, that is to say to a lower hysteresis, which is why one also speaks of low hysteresis carbon blacks. Carbon blacks of this type, and processes for their production, are described in patent specifications EP 0 315 442 and EP 0 519 988.

DE 19521565 discloses furnace carbon blacks having CTAB values from 80 to 180 m²/g and 24M4-DBP absorption from 80 to 140 ml/100 g, for which, in the case of incorporation into an SSBR/BR rubber mixture, a $\tan\delta_0/\tan\delta_{60}$ ratio of

$$\tan\delta_0/\tan\delta_{60} > 2.76 - 6.7 \times 10^{-3} \times \text{CTAB}$$

applies and the $\tan\delta_{60}$ value is always lower than the value for ASTM carbon blacks having the same CTAB surface area and 24M4-DBP absorption. In that process, the fuel is burnt with a smoking flame in order to form seeds.

SUMMARY OF THE INVENTION

The object of the present invention is to produce a carbon black that has a higher activity when used as a support material for electrocatalysts in fuel cells.

The invention provides a furnace carbon black, characterized in that it has a hydrogen (H) content of greater than 4000 ppm, determined by CHN analysis, and a peak integral ratio, determined by inelastic neutron scattering (INS), of non-conjugated H atoms (1250-2000 cm⁻¹) to aromatic and graphitic H atoms (1000-1250 cm⁻¹ and 750-1000 cm⁻¹) of less than 1.22.

The H content may be greater than 4200 ppm, preferably greater than 4400 ppm. The peak integral ratio of non-conjugated H atoms (1250-2000 cm⁻¹)

to aromatic and graphitic H atoms ($1000-1250\text{ cm}^{-1}$ and $750-1000\text{ cm}^{-1}$) may be less than 1.20.

The CTAB surface area may be from 20 to $200\text{ m}^2/\text{g}$, preferably from 20 to $70\text{ m}^2/\text{g}$. The DBP number may be from 40 to 160 ml/100 g, preferably from 100 to 140 ml/100 g.

The very high hydrogen content indicates a pronounced disturbance of the carbon lattice by an increased number of crystallite edges.

The invention further provides a process for the production of the furnace carbon black according to the invention in a carbon black reactor which contains, along the axis of the reactor, a combustion zone, a reaction zone and a termination zone, by producing a stream of hot waste gas in the combustion zone by completely burning a fuel in an oxygen-containing gas and passing the waste gas from the combustion zone through the reaction zone into the termination zone, mixing a carbon black raw material with the hot waste gas in the reaction zone and stopping the formation of carbon black in the termination zone by spraying in water. The process is characterized in that a liquid carbon black raw material and a gaseous carbon black raw material are injected at the same point.

The liquid carbon black raw material may be atomized by pressure, steam, compressed air or the gaseous carbon black raw material.

Liquid hydrocarbons burn more slowly than gaseous hydrocarbons since they must first be converted into the gaseous form, i.e., they must be vaporized. As a result, the carbon black contains components that are formed from the gas and components that are formed from the liquid.

The so-called K factor is frequently used as the measurement value for characterizing the excess of air. The K factor is the ratio of the amount of air required for stoichiometric combustion of the fuel to the amount of air actually supplied to the combustion. A K factor of 1, therefore, means stoichiometric combustion. Where there is an excess of air, the K factor is less than 1. K factors of from 0.3 to 0.9 may be applied, as in the case of known carbon blacks. K factors of from 0.6 to 0.7 are preferably used.

Liquid aliphatic or aromatic, saturated or unsaturated hydrocarbons or mixtures thereof, distillates from coal tar or residue oils which are formed in the

catalytic cracking of crude oil fractions or in the production of olefins by cracking naphtha or gas oil, may be used as the liquid carbon black raw material.

5 Gaseous aliphatic, saturated or unsaturated hydrocarbons, mixtures thereof or natural gas may be used as the gaseous carbon black raw material.

The process described is not limited to a particular reactor geometry. Rather, it may be adapted to different types of reactor and sizes of reactor.

10 The carbon black raw material atomizers used may be both pure mechanical atomizers (single-component atomizers) and two-component atomizers with internal or external mixing. It is possible for the gaseous carbon black raw material to be used as the atomizing medium. The above-described combination of a liquid and a gaseous carbon black raw material may therefore be implemented, for example, by using the gaseous carbon black raw material as the atomizing medium for the liquid carbon black raw material.

15 Two-component atomizers may preferably be used for atomizing the liquid carbon black raw material. While in the case of single-component atomizers, a change in the throughput may also lead to a change in the droplet size, the droplet size in the case of two-component atomizers can be influenced largely independently of the throughput.

20 Using the process according to the invention it is possible to produce the entire range of industrial furnace carbon blacks. The measures necessary therefor, such as, for example, the setting of the dwell time in the reaction zone and the addition of additives to influence the structure of the carbon black, are known to a person skilled in the art.

25 **BRIEF DESCRIPTION OF THE DRAWINGS**

Figure 1 illustrates, schematically, a carbon black reactor used in a process of the invention.

Figure 2 illustrates, schematically, an axial lance having nozzleheads, used in a process of the invention.

30

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Examples

In the Examples and Comparative Examples that follow, furnace carbon blacks according to the invention are produced and their use as a support material for electrocatalysts is described. The electrochemical performance data in a fuel cell are used as the criterion for evaluating the furnace carbon blacks.

Production of carbon black B1:

A carbon black according to the invention is produced in the carbon black reactor 1 shown in Figure 1. The carbon black reactor 1 has a combustion chamber 2. The oil which is the liquid carbon black raw material and the gas which is the gaseous carbon black raw material are introduced into the combustion chamber through the axial lance 3. The lance may be displaced in the axial direction in order to optimize carbon black formation.

The combustion chamber leads to a narrow portion 4. After passing through the narrow portion, the reaction gas mixture expands into the reaction chamber 5.

The lance has suitable spray nozzles at its head (Figure 2).

The combustion zone, the reaction zone and the termination zone, which are important for the process according to the invention, cannot be separated sharply from one another. Their axial extent depends on the positioning of the lances and the quenching water lance 6 in each particular case.

The non-limiting dimensions of an exemplary reactor used are as indicated below:

largest diameter of the combustion chamber:	696 mm
length of the combustion chamber to the narrow portion:	630 mm
diameter of the narrow portion:	140 mm
length of the narrow portion:	230 mm
diameter of the reaction chamber:	802 mm

position of the oil lances ¹⁾ + 160 mm
position of the quenching water lances ¹⁾ 2060 mm
¹⁾ measured from the zero point (beginning of the narrow portion)

The reactor parameters for the production of the carbon black according
5 to the invention are listed in the table below.

Reactor parameters Parameter	Carbon black	
	Unit	B1
Combustion air	Nm ³ /h	1500
Combustion air temperature	°C	550
Σ natural gas	Nm ³ /h	156
k factor (total)		0.70
Carbon black oil, axial	kg/h	670
Carbon black oil position	mm	+16
Atomizing vapor	kg/h	100
Additive (K ₂ CO ₃ solution)	l/h x g/l	5.0 x 3.0
Additive position		axial
Reactor outlet	°C	749
Quenching position	mm	9/8810

Characterization of carbon black B1:

The hydrogen content of the carbon blacks is determined by CHN
10 elemental analysis (LECO RH-404 analyzer with thermal conductivity detector).
The method of inelastic neutron scattering (INS) is described in the literature
(P. Albers, G. Prescher, K. Seibold, D. K. Ross and F. Fillaux, *Inelastic Neutron
Scattering Study Of Proton Dynamics In Carbon Blacks*, Carbon 34 (1996) 903
and P. Albers, K. Seibold, G. Prescher, B. Freund, S. F. Parker, J. Tomkinson,
15 D. K. Ross, F. Fillaux, *Neutron Spectroscopic Investigations On Different
Grades Of Modified Furnace Blacks And Gas Blacks*, Carbon 37 (1999) 437).

The INS (or IINS - inelastic incoherent neutron scattering) method offers some quite unique advantages for the more intensive characterization of carbon blacks and activated carbons.

In addition to the proven elemental-analytical quantification of the H content, the INS method allows the in some cases very small hydrogen content in graphitized carbon blacks (about 100-250 ppm), carbon blacks (about 2000-4000 ppm in furnace carbon blacks) and in activated carbons (about 5000-12000 ppm in typical catalyst supports) to be broken down in greater detail in respect of its bond states.

The table below lists the values of the total hydrogen content of the carbon blacks, determined by CHN analysis (LECO RH-404 analyzer with thermal conductivity detector). In addition, the spectra integrals are given, which are determined as follows: integration of the regions of an INS spectrum of 750-1000 cm^{-1} (A), 1000-1250 cm^{-1} (B) and 1250-2000 cm^{-1} (C). The aromatic and graphitic H atoms are formed by the sum of the peak integral A and B.

The carbon blacks are introduced without further pretreatment into specially developed aluminum (Al) cuvettes (Al having a purity of 99.5 %, cuvette wall thickness 0.35 mm, cuvette diameter 2.5 cm). The cuvettes are hermetically sealed (flange gasket from Kalrez O-ring).

Carbon black	H content [ppm] by CHN elemental analysis	Peak integral by INS measurements			Ratio C/ (A+B)
		A	B	C	
		750-1000cm ⁻¹ out of plane C-H- deformation vibration	1000-1250cm ⁻¹ in plane C-H- deformation vibration	1250-2000cm ⁻¹ C-H- deformation vibration of non-conjugated constituents	non-conjugated H atoms to aromatic and graphitic H atoms
B1	4580 ± 300	107 ± 1	99 ± 1	241 ± 3	1.17
N 234	3853	23.2 ± 1	21.4 ± 1	55 ± 3	1.23
EB 111 (DE 19521565)	4189	27.4 ± 1	26.1 ± 1	68 ± 3	1.27
Vulcan XC-72 Furnace carbon black	2030 ± 200	69 ± 1	63 ± 1	176 ± 3	1.33

Accordingly, carbon black B1 exhibits quantitatively more hydrogen relative to the other carbon blacks, but its sp^3/sp^2 -H ratio is lower, that is to say the additional amount of hydrogen is bonded especially

5 aromatically/graphitically. There are C-H- protons at cleavage edges and defects saturated with hydrogen, and hence the surface is on average more greatly disturbed. Nevertheless, carbon black B1, when considered in absolute terms, at the same time also has the highest proportion of disturbed, non-conjugated constituents, without on the other hand - in relative terms - its

10 sp^3/sp^2 nature being drastically altered in the direction of sp^3 .

The surface area ratio of the specific surface areas BET adsorption by CTAB (cetylammonium bromide) adsorption is determined according to standard DIN 66 132.

Carbon black	CTAB surface area [m ² /g]	BET surface area [m ² /g]	BET:CTAB surface area ratio
B1	30	30	1

Example 1

20.1 g of carbon black B1 (0.5 wt.% moisture) are suspended in 2000 ml of demineralized water. After heating to 90°C and adjustment of the pH value to 9 using sodium hydrogen carbonate, 5 g of platinum in the form of hexachloro-
 5 platinumic acid solution (25 wt.% Pt) are added, and the suspension is adjusted to pH 9 again, reduced with 6.8 ml of formaldehyde solution (37 wt.%), washed, after filtration, with 2000 ml of demineralized water and dried *in vacuo* for 16 hours at 80°C. The resulting electro-catalyst has a platinum content of 20 wt.%.

10 Comparative Example 1

Analogously to Example 1, 20.0 g of carbon black Vulcan XC-72 R (based on dry weight) from Cabot are suspended in 2000 ml of demineralized water. The electrocatalyst is prepared in the same manner as described in Example 1. After drying *in vacuo*, an electrocatalyst having a platinum content of 20 wt.% is
 15 obtained.

Example 2

A solution of 52.7 g of hexachloroplatinic acid (25 wt.% Pt) and 48.4 g of ruthenium(III) chloride solution (14 wt.% Ru) in 200 ml of deionized water is added, with stirring, at room temperature, to a suspension of 80.4 g of carbon
 20 black B1 (0.5 wt.% moisture) in 2000 ml of demineralized water. The mixture is heated to 80°C and the pH value is adjusted to 8.5 using sodium hydroxide solution. After the addition of 27.2 ml of a formaldehyde solution (37 wt.%), the mixture is filtered off and washed with 2000 ml of demineralized water, and the

moist filter cake is dried at 80°C in a vacuum drying cabinet. An electrocatalyst containing 13.2 wt.% platinum and 6.8 wt.% ruthenium is obtained.

Comparative Example 2

Analogously to Example 2, using 81.1 g of carbon black Vulcan XC-72 R
5 (1.39 wt.% moisture) as catalyst support, a platinum/ruthenium catalyst containing 13.2 wt.% Pt and 6.8 wt.% Ru is obtained.

The synthesis of Comparative Example 2 is described in DE 197 21 437, in Example 1.

For the purpose of electrochemical characterization, the electrocatalysts
10 are processed to form a membrane electrode assembly (MEA). The electrocatalyst according to the invention of Example 1 and the electrocatalyst of Comparative Example 1 are characterized as cathode catalysts in hydrogen/air and hydrogen/oxygen operation. The electrocatalyst according to the invention of Example 2 and the electrocatalyst of Comparative Example 2
15 are tested as CO-tolerant anode catalysts in reformat/oxygen operation.

The cathode and anode catalysts are applied to an ion-conductive membrane (Nafion 115) according to Example 1 of the process described in U.S. 5,861,222. The membrane so coated is placed between two carbon papers (TORAY, TCG 90) which have been rendered hydrophobic in a
20 conductive manner. The coating on the cathode and anode sides is in each case 0.25 mg of platinum/cm². The resulting membrane electrode assembly (MEA) is measured in a PEM single cell (pressureless operation, temperature 80°C), a current density of 0.4 A/cm² being set.

For the electrochemical testing of the cathode catalysts, both sides of the
25 membrane are coated with a paste of a platinum catalyst described in Example 1 or Comparative Example 1.

Oxygen or air is used as the fuel gas on the cathode, and hydrogen is used on the anode.

Catalyst	Cell performance at 400 mA/cm ² [mV]		Cell performance at 500 mA/cm ² [mV]	
	O ₂	air	O ₂	air
Example 1	687	606	649	545
Comparative Example 1	630	518	576	429

The preparation of a membrane electrode assembly for testing the anode catalyst is carried out completely analogously to the process according to U.S. Patent No. 5,861,222 described for the cathode catalysts.

5 In that case, a supported Pt/Ru catalyst prepared according to Example 2 or Comparative Example 2 is used as the anode catalyst. On the cathode side, a platinum catalyst prepared according to Comparative Example 1 is used in both membrane electrode assemblies.

10 Measurement is carried out in a PEM single cell (operation with pressure at 3 bar, temperature 75°C), a current density of 0.5 A/cm² being set.

The cell voltage U in hydrogen/oxygen operation (without the metering in of reformat and/or CO on the anode side) is used as a measure of the catalyst activity.

15 The voltage drop ΔU , which occurs after the metering in of 100 ppm of CO to the fuel gas, is used as a measure of the CO tolerance of the catalyst.

The following fuel gas composition in reformat/CO operation is used: 58 vol.% H₂; 15 vol.% N₂, 24 vol.% CO₂, 3 vol.% air ("airbleed").

Catalyst	H ₂ /O ₂ operation: cell performance at 500 mA/cm ² [mV]	Reformate/O ₂ operation: cell performance at 500 mA/cm ² [mV]	ΔU CO-induced voltage drop [mV]
Example 2	715	661	- 54
Comparative Example 2	686	620	- 66

The cell performance is markedly increased for Examples 1 and 2 as compared with the respective comparative examples.

WHAT IS CLAIMED IS:

1. Furnace carbon black, having a hydrogen (H) content of greater than 4000 ppm, determined by CHN analysis, and a peak integral ratio, determined by inelastic neutron scattering (INS), of non-conjugated H atoms (1250-2000
5 cm^{-1}) to aromatic and graphitic H atoms (1000-1250 cm^{-1} and 750-1000 cm^{-1}) of less than 1.22.

2. A process for the production of furnace carbon black according to claim 1 in a carbon black reactor which contains, along the axis of the reactor, a combustion zone, a reaction zone and a termination zone, comprising:

10 producing a stream of hot waste gas in the combustion zone by completely burning a fuel in an oxygen-containing gas and passing the waste gas from the combustion zone through the reaction zone into the termination zone,

mixing carbon black raw material into the hot waste gas in the reaction
15 zone and stopping carbon black formation in the termination zone by spraying in water,

wherein the carbon black raw material comprises liquid carbon black raw material and gaseous carbon black raw material that are injected at the same point.
20

3. A process according to claim 2, wherein the liquid carbon black raw material and the gaseous carbon black raw material are introduced at the same point through a lance.

25 4. A process according to claim 3, wherein the lance comprises spray nozzles.

5. A process for using the furnace carbon black according to claim 1, comprising:

incorporating the furnace carbon black into electrocatalysts during preparation thereof.

ABSTRACT OF THE DISCLOSURE

Furnace carbon black which has a hydrogen (H) content of greater than 4000 ppm and a peak integral ratio of non-conjugated H atoms (1250-2000
5 cm^{-1}) to aromatic and graphitic H atoms (1000-1250 cm^{-1} and 750-1000 cm^{-1}) of less than 1.22. The furnace carbon black is produced by injecting the liquid carbon black raw material and the gaseous carbon black raw material at the same point in a furnace carbon black process. The furnace carbon black may be used in the preparation of electrocatalysts.

Figure 1




Figure 2